

Chemical Resistance

Klinger gasket materials can be select from the following table. The following information should be used as a guide only. Please contact our Technical Services Department if in any doubt.

✓ Suitable
 ✓ Suitability depends on operating conditions
 ✗ Unsuitable

Media	Formula	C-4400	C-4430	C-4500	C-4509	C-8200	C-4324	Top-Graph 2000	Graphite	Topchem 2005	Topchem 2006	Milam PSS / Mica
A												
Acetaldehyde	CH ₃ CHO	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Acetamide	CH ₃ COCH ₂	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Acetic acid 10%	CH ₂ COOH	✓	✓	✓	✗	✓	✓	✓	✓	✓	✓	✓
Acetic acid 100%	CH ₂ COOH	✓	✓	✓	✗	✓	✓	✓	✓	✓	✓	✓
Acetic ether	CH ₃ COOC ₂ H ₅	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Acetone	CH ₃ COCH ₃	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Acetylene	C ₂ H ₂	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Adipic acid	COOH(CH ₂) ₄ COOH	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Alum	KAl(SO ₄) ₂	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Aluminium acetate	(CH ₃ COO) ₃ Al	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Aluminium chlorate	Al(ClO ₃) ₃	✓	✓	✓	✗	✓	✓	✓	✓	✓	✓	✓
Aluminium chloride	AlCl ₃	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Ammonia	NH ₃	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Ammonium bicarbonate	NH ₄ HCO ₃	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Ammonium chloride	NH ₄ Cl	✓	✓	✓	✗	✓	✓	✓	✓	✓	✓	✓
Ammonium diphosphate	(NH ₄) ₂ HPO ₄	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Ammonium hydroxide	NH ₄ OH	✓	✓	✓	✓	✓	✗	✓	✓	✓	✓	✓
Amyl acetate	CHCOOC ₅ H ₁₁	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Aniline	C ₆ H ₅ NH ₂	✗	✗	✗	✗	✗	✗	✗	✓	✓	✓	✓
Asphalt (tar)		✓	✓	✓	✓	✓	✓	✗	✓	✓	✓	✓
ASTM oil 1		✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
ASTM oil 3		✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
B												
Barium chloride	BaCl ₂	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Benzene	C ₆ H ₆	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Benzine		✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Benzoic acid	C ₆ H ₅ COOH	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Bleach	Ca(OCl) ₂	✓	✓	✓	✗	✓	✓	✓	✓	✓	✓	✓
Borax	Na ₂ B ₄ O ₇ 10H ₂ O	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Boric Acid	H ₃ BO ₃	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Brine	NaCl	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Butane	C ₄ H ₁₀	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Butanone	M.E.K.	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Butyl acetate	CHCOOC ₄ HP	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓

Media	Formula	C-4400	C-4430	C-4500	C-4509	C-8200	C-4324	Top-Graph 2000	Graphite	Topchem 2005	Topchem 2006	Milam PSS / Mica
Butyl alcohol (butanol)	C ₄ H ₉ OH	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Butyric acid	C ₃ H ₇ COOH	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
C												
Calcium chloride	CaCl ₂	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Calcium hydroxide	Ca(OH) ₂	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Calcium hypochlorite	Ca(OCl) ₂	✓	✓	✓	✗	✓	✓	✓	✓	✓	✓	✓
Calcium sulphate	CaS ₀₄	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Carbolic acid 100%	C ₆ H ₅ OH	✗	✗	✗	✗	✓	✗	✗	✓	✓	✓	✓
Carbon dioxide	CO ₂	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Carbon disulphide	CS ₂	✗	✗	✓	✗	✗	✗	✓	✓	✓	✓	✓
Carbon tetrachloride	CCl ₄	✓	✓	✓	✓	✗	✓	✓	✓	✓	✓	✓
Castor oil		✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Chlorine (dry)	Cl ₂	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Chlorine water (0,5%)		✓	✓	✓	✗	✓	✓	✓	✓	✓	✓	✓
Chlorine (wet)	Cl ₂	✗	✗	✗	✗	✗	✗	✓	✓	✓	✓	C
Chloroform	CHCl ₃	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Chloromethane	CH ₃ Cl	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Chromic acid	H ₂ CrO ₄	✓	✓	✓	✗	✓	✗	✓	✗	✓	✓	✓
Citric acid	(CH ₂ COOH) ₂ C(OH)COOH	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Clophen	T ₆₄	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	-
Copper acetate	(CH ₃ COO) ₂ Cu	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Copper sulphate	CuS ₄	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Creosote		✗	✗	✗	✗	✗	✗	✗	✓	✓	✓	-
Cresol	C ₆ H ₄ (OH)CH ₃	✓	✓	✓	✓	✗	✓	✗	✓	✓	✓	✓
Cyclohexanol	C ₆ H ₁₁ OH	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Cyclohexanone	C ₅ H ₁₀ O	✗	✗	✗	✗	✗	✗	✗	✓	✓	✓	-
D												
Decalin	C ₁₀ H ₁₈	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Diammonium phosphate	(NH ₄) ₂ HPO ₄	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	-
Di-benzylether	(C ₆ H ₅ CH ₂) ₂ O	✗	✗	✗	✗	✗	✗	✗	✓	✓	✓	-
Di-butylphthalate	C ₆ H ₄ (COOC ₄ H ₉) ₂	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Diesel oil		✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Dimenthylformamide	HCON(CH ₃) ₂	✗	✗	✗	✗	✗	✗	✗	✓	✓	✓	-
Diphyl (Dowtherm A)		✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Dye Liquor		✓	✓	✓	✗	✓	✓	✓	✓	✓	✓	✓
E												
Ethane	C ₂ H ₆	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Ethyl acetate	CH ₃ COOC ₂ H ₅	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Ethyl alcohol (Ethanol)	C ₂ H ₅ OH	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Ethyl chloride	C ₂ H ₅ Cl	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Ethyl ether	C ₂ H ₅ OC ₂ H ₅	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Ethylene chloride	(CH ₂ Cl) ₂	✗	✗	✗	✗	✓	✗	✗	✓	✓	✓	✓
Ethylene glycol	(CH ₂ OH) ₂	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
F												
Fluosilicic acid	H ₂ SiF ₆	✓	✓	✓	✗	✓	✓	✓	✓	✓	✓	✓
Formaldehyde	HCNHO	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Formamide	CHCONH ₂	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Formic acid 10%	HCOOH	✓	✓	✓	✗	✓	✓	✓	✓	✓	✓	✓

Media	Formula	C-4400	C-4430	C-4500	C-4509	C-8200	C-4324	Top-Graph 2000	Graphite	Topchem 2005	Topchem 2006	Milam PSS / Mica
Formic acid 85%	HCOOH	✓	✓	✓	✗	✓	✓	✓	✓	✓	✓	✓
Freon 12		✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Freon 22		✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
G												
Glacial acetic acid	CH ₃ COOH	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Glucose		✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Glycerine	(CH ₂ OH) ₂ CHOH	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
H												
Heating oil		✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Heptane	C ₇ H ₁₆	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Hydraulic oil (mineral/Glycol)		✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Hydraulic oil (phosphate ester)		✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Hydrazine hydrate	(NH ₂) ₂ H ₂ O	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Hydrochloric acid 20%	HCl	✓	✓	✓	✗	✓	✓	✓	✓	✓	✗	✓
Hydrochloric acid 30%	HCl	✗	✗	✗	✗	✓	✗	✗	✓	✓	✗	✓
Hydrofluoric acid (10%)	HF	✗	✗	✗	✗	✓	✗	✗	✓	✓	✗	✓
Hydrogen	H ₂	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Hydrogen peroxide (<6%w.w.)		✗	✗	✗	✗	✗	✗	✗	✓	✓	✓	✓
I												
Iso-octane	(CH ₃) ₃ CCH ₂ (CH ₃) ₂	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Iso-propyl alcohol	(CH ₃) ₂ CHOH	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
K												
Kerosene (petroleum)		✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
L												
Lactic acid 50%	CH ₃ CHOHCOOH	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Lead acetate	(CH ₃ COO) ₂ Pb	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Lead arsenate	Pb ₃ (AsO ₄) ₂	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Lime water	Ca(OH) ₂	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Linseed oil		✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
M												
Magnesium sulphate	MgSO ₄	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Maleic acid	HOOCCH ₂ CHOHCOOH	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Methane	CH ₄	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Methyl alcohol	CH ₃ OH	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Methyl chloride	CH ₃ Cl	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Methyl ethyl ketone	CH ₃ COO ₂ H ₅	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Methylated spirits		✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Methylene chloride	CH ₂ Cl ₂	✗	✗	✓	✗	✗	✗	✗	✓	✓	✓	-
Mineral oil - ASTM No. 1		✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Mineral oil - ASTM No. 3		✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
N												
Naphtha		✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Natural gas (Methane)	CH ₄	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Nitric acid 20%	HNO ₃	✗	✗	✗	✗	✓	✗	✗	✓	✓	✓	✓
Nitric acid 40%	HNO ₃	✗	✗	✗	✗	✓	✗	✗	✓	✓	✓	-
Nitric acid 96%	HNO ₃	✗	✗	✗	✗	✗	✗	✗	✓	✓	✗	-
Nitrobenzene	C ₆ H ₅ NO ₂	✗	✗	✗	✗	✗	✗	✗	✓	✓	✓	-
Nitrogen	N ₂	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓

Media	Formula	C-4400	C-4430	C-4500	C-4509	C-8200	C-4324	Top-Graph 2000	Graphite	Topchem 2005	Topchem 2006	Milam PSS / Mica
O												
Octane	C ₈ H ₁₈	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Oleic acid	C ₁₇ H ₃₃ COOH	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Oleum (fuming sulphuric acid)		✗	✗	✗	✗	✗	✗	✗	✗	✓	✓	✗
Oxalic acid	(COOH) ₂	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Oxygen	O ₂	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
P												
Palmitic acid	C ₁₅ H ₁₅ COOH	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Paraffin		✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Pentane	C ₅ H ₁₂	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Perchloroethylene	C ₂ Cl ₄	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Petrol		✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Petroleum ether		✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Phenol	C ₆ H ₅ OH	✗	✗	✗	✗	✓	✗	✗	✓	✓	✓	✓
Phosphoric acid	H ₃ PO ₄	✓	✓	✓	✗	✓	✗	✓	✓	✓	✓	✓
Phthalic acid	(C ₆ H ₄ COOH) ₂	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Potassium acetate	CH ₃ COOK	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Potassium carbonate	K ₂ CO ₃	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Potassium chlorate	KClO ₃	✓	✓	✓	✗	✓	✓	✓	✓	✓	✓	✓
Potassium chloride	KCl	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Potassium chromium sulphate	KCr(SO ₄) ₂ H ₂ O	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Potassium cyanide	KCN	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Potassium dichromate	K ₂ Cr ₂ O ₇	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Potassium hydroxide	KOH	✓	✓	✓	✓	✓	✓	✓	✓	✗	✓	✓
Potassium hypochlorite	KClO	✓	✓	✓	✗	✓	✓	✓	✓	✓	✓	✓
Potassium iodide	KI	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Potassium nitrate	KNO ₃	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Potassium permanganate	KMnO ₄	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Propane	C ₃ H ₈	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Pydrol		✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Pyridine	C ₅ H ₅ N	✗	✗	✗	✗	✗	✗	✗	✓	✓	✓	-
S												
Salicylic acid	C ₆ H ₄ (OH)COOH	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Salt	NaCl	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Sea water		✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Silicone oil		✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Skydrol 500		✗	✗	✗	✗	✗	✗	✗	✓	✓	✓	-
Soda	Na ₂ CO ₃	✓	✓	✓	✓	✓	✓	✓	✓	✓	✗	✓
Sodium aluminate	Na ₃ AlO ₃	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Sodium bisulphite	NaHSO ₃	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Sodium bicarbonate	NaHCO ₃	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Sodium chloride	NaCl	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Sodium cyanide	NaCN	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Sodium hydroxide	NaOH	✓	✓	✓	✓	✓	✓	✓	✓	✗	✓	✓
Sodium silicate (water glass)		✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Sodium sulphate	Na ₂ SO ₄	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Sodium sulphide	Na ₂ S	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Steam	H ₂ O	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓

Media	Formula	C-4400	C-4430	C-4500	C-4509	C-8200	C-4324	Top-Graph 2000	Graphite	Topchem 2005	Topchem 2006	Milam PSS / Mica
Stearic acid	$C_{17}H_{35}COOH$	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Sulphur dioxide	SO_2	✗	✗	✓	✗	✓	✗	✓	✓	✓	✓	✓
Sulphuric acid 30%	H_2SO_4	✗	✗	✗	✗	✓	✗	✗	✓	✓	✗	✓
Sulphuric acid 50%	H_2SO_4	✗	✗	✗	✗	✓	✗	✗	✓	✓	✗	-
Sulphuric acid 96%	H_2SO_4	✗	✗	✗	✗	✓	✗	✗	✗	✓	✗	-
Sulphurous acid	H_2SO_3	✓	✓	✓	✗	✓	✓	✓	✓	✓	✓	✓
T												
Tannic acid	$C_{76}H_{52}O_{46}$	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Tar (Asphalt)		✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Tartaric acid	$(CHOH COOH)_2$	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Tetrachloroethane	$C_2H_2Cl_4$	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Tetraline	$C_{10}H_{12}$	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Toluene	$C_6H_5CH_3$	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Transformer oil		✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Trichloroethylene	C_2HCl_3	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Triethanolamine	$N(CH_2CH_2OH)_3$	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Turpentine		✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
U												
Urea	$(NH_2)_2CO$	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
V												
Vinyl acetate	$CH_3COOC_2H_3$	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
W												
Water	H_2O	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
Water glass	$Na_2SiO_3K_2SiO_3$	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
White spirit		✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
X												
Xylol	$C_6H_4(CH_3)_2$	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓

All information and recommendations contained in this publication are to the best of our knowledge correct. Since conditions of use are beyond our control users must satisfy themselves that products are suitable for the intended processes and uses. No warranty is given or implied in respect of information or recommendations or that any use of products will not infringe rights belonging to other parties. In any event or occurrence our liability is limited to our invoice value of the goods delivered by us to you. We reserve the right to change product design and properties without notice.