

Ceramic Fibre Packing

Ceramic Packing

Ceramic packings are suited for high temperature low pressure applications where poor flanges or low bolt loadings are present. Typical applications are for ductwork flange gasketing, furnace / boiler door seals and Kiln seals.

Construction

Ceramic fibre packings are manufactured from high performance ceramic fibre yarns reinforced with either a wire or glass filament. Ceramic fibre yarns are produced on traditional textile machinery by carding high purity 1260°C ceramic fibres with a percentage of cellulose fibre to assist in the processing. The yarns are then spun and combined with the relevant reinforcing media to improve the tensile strength at extended temperatures. The organic content will burn off at temperatures above 200°C without affecting the properties of the ceramic fibre, adequate ventilation should be provided during this initial heating.

Where tensile strength is important the temperature limitations of the reinforcing media should be considered.

The Klinger group has been recognised as the market leader in gaskets and sealing for over a century. Our research and development laboratories have investigated over 250 different fibre forms in the search for asbestos free alternatives. The search has resulted in a range of high quality and high performance asbestos free materials that have been proven in service

General Properties

- Suitable for ductwork flange gasketing, furnace / boiler door seals and Kiln seals
- Colour White

Ceramic Fibres

- Ceramic fibres are non combustible
- Suitable for temperatures up to 1260° C (material max temp dependent on reinforcement).

Reinforcement Temperature Limitations:

Glass Filament	Suitable up to 550°C
Nickel Chrome wire	Suitable up to 1091° C

Chemical Resistance

Ceramic fibres are resistant to oils, solvents and most chemicals, however contact with Phosphoric, Hydrofluoric acids and strong alkalis should be avoided.

Availability

- Square or round section.



Head Office
KLINGER Ltd
Wharfedale Road
Euroway Trading Estate
Bradford BD4 6SG

Tel: 01274 688 222
Fax: 01274 688 549

Klinger Ltd. Grangemouth
Tel: 01324 472 231
Fax: 01324 482 111

Klinger Ltd. Aberdeen
Tel: 01224 772 962
Fax: 01224 772 953

Klinger Ltd. Middlesbrough
Tel: 01642 220 289
Fax: 01642 220 290

Klinger Ltd. Runcorn
Tel: 01928 577 030
Fax: 01928 575 223

Klinger Ltd. International
Tel: 020 8308 0100
Fax: 020 8308 0200