

TECHNICAL DATA SHEET

PTFE G405

Properties	Unit	Method	Data - Moulded
<b>PHYSICAL - MECHANICAL</b>			
Density	g/cm <sup>3</sup>	ASTM D792	2,20 - 2,26
Hardness - Shore D	/	ASTM D2240	≥ 60
Tensile Strength - CD	N/mm <sup>2</sup>	ISO 12086 ISO 527	≥ 17
Elongation at break - CD	%	ISO 12086 ISO 527	≥ 230
Compressive strength at 1% deformation - CD	N/mm <sup>2</sup>	ASTM D695	8 - 9
Deformation under load at room temperature 24 Hours at 13,7 N/mm <sup>2</sup> - CD	%	ASTM D621	≤ 10
Permanent deformation as above after releasing of 24 hours at room temperature - CD	%	ASTM D621	≤ 6,5
<b>TRIBOLOGICAL</b>			
Dynamic coefficient of friction	/	ASTM D1894 ASTM D3702	0,15 - 0,3
Wear factor	/	ASTM D3702	0,015 - 0,030
<b>THERMAL</b>			
Service Temperature (min - max)	°C	/	- 200 / + 260
Thermal expansion coefficient (linear) 25 - 100°C	10 <sup>-5</sup> (mm/mm)/ °C	Similar to ASTM D696	7,5 - 11
<b>ELECTRICAL</b>			
Volume Resistivity	Ω • cm	ASTM D257	> 10 <sup>15</sup>
Surface Resistivity	Ω	ASTM D257	> 10 <sup>15</sup>

CD = cross direction

The data we are herewith providing are all based on laboratory testing and are proposed to technical designers as possible and useful advice. Deviations from the values hereabove indicated may occur, but they do not constitute themselves either detriment of quality or reason for rejection.

REV. 06

January 2012



Guarniflon S.p.A.  
PTFE Products Division  
Via T.Tasso 12 - 24060 Castelli Calepio (BG) IT  
Phone +39.035.4494311

Domestic Dept. Fax +39.035.4425191  
Export Dept. Fax +39.035.4425238

VAT N. IT 01406020162 - Reg. Imp. BG  
REA N. 203233 - Cod.Mecc. BG 003351  
Cap. Sociale € 10.000.000 interamente versato

PTFE Finished and Semifinished Products  
http://www.guarniflon.com | info@guarniflon.com  
Accounting Dept. Fax +39.035.4425249



UNI EN ISO 9001:2008

