

Description:

PG-M is a high performance compressed sheet material based upon mica and aramid fibre with a small volume of elastomeric binder.

Application:

PG-M is designed to operate at higher temperatures than conventional sheet jointing material. It has excellent residual stress properties and meets the requirements of BS 7531 Grade X.

Availability:**Thickness**

0.5mm to 6.0mm

Sheet Size

1500mm X 1500mm, 4500mm X 1500mm


1900mm X 1900mm, 3800mm X 3800mm

Specification:


BS7531 Grade X

Colour: Gold

PG-M Datasheet

**Typical Physical Properties:**

Thickness		1.5mm
Density		1.84 g/cc
Tensile Strength	ASTM F152	13 MPa
Compression	ASTM F36 J	7% to 15%
Recovery	ASTM F36 J	56%
Residual Stress	BS7531 (40N/mm ² @ 300°C)	26 MPa
Gas Leakage	BS7531	0.2 ml/min
ASTM Oil 1	ASTM F146	2.5%
ASTM Oil 3	ASTM F146	4.0%
ASTM Fuel B	ASTM F146	4.0%

Service:

A = Suitable subject to chemical compatibility.

B = Please contact our Technical Team.

C = Not Suitable

As the company's products are used in multiple applications and as the company has no control over the method of their use, the company excludes all conditions or warranties, expressed or implied by statute or otherwise. Any technical cooperation is given for customer assistance only and without liability on the part of the company.

