

GLASS FILLED 25%



PROPERTY	UNITS	METHOD	SPECIFICATIONS	VALUES
Specific gravity	g / cm ³	DIN 53479	nd	2,2292
Tensile CD	N / mm ²	ASTM D4745-97	nd	19
Elongation CD	%	ASTM D4745-97	nd	183
Hardness 1	Shore D	DIN 53505	nd	58,8-60,2
Hardness 2	N / mm ²	DIN ISO 2039	nd	nd
Bulk density	g / It	ASTM 4894	nd	778
Shrink	%	INTERNAL	nd	0,84
Filler content	%	FLONTECH TGA	nd	nd
Melting point	°C	FLONTECH DSC	nd	nd
Flow	Sec / 50g	INTERNAL	nd	3
Flow stbility	Sec / 50g	INTERNAL	nd	3
Volum res	Ω cm	DIN IEC 93	nd	nd
Surface res	Ω	DIN IEC 93	nd	nd
Pellet size	µm	SCREEN FISHER	nd	1200
Particle Size Distr		Internal	nd	nd



J.A. Harrison

Complete Sealing Solutions

jaharrison.co.uk