



Properties	Unit	Method	Data - Moulded
PHYSICAL - MECHANICAL			
Density	g/cm ³	ASTM D792	2,20 - 2,26
Hardness - Shore D	/	ASTM D2240	≥ 60
Tensile Strength - CD	N/mm ²	ISO 12086 ISO 527	≥ 17
Elongation at break - CD	%	ISO 12086 ISO 527	≥ 230
Compressive strength at 1% deformation - CD	N/mm ²	ASTM D695	8 - 9
Deformation under load at room temperature 24 Hours at 13,7 N/mm ² - CD	%	ASTM D621	≤ 10
Permanent deformation as above after releasing of 24 hours at room temperature - CD	%	ASTM D621	≤ 6,5
TRIBOLOGICAL			
Dynamic coefficient of friction	/	ASTM D1894 ASTM D3702	0,15 - 0,3
Wear factor	/	ASTM D3702	0,015 - 0,030
THERMAL			
Service Temperature (min - max)	°C	/	- 200 / + 260
Thermal expansion coefficient (linear) 25 - 100°C	10 ⁻⁵ (mm/mm)/ °C	Similar to ASTM D696	7,5 - 11
ELECTRICAL			
Volume Resistivity	Ω • cm	ASTM D257	> 10 ¹⁵
Surface Resistivity	Ω	ASTM D257	> 10 ¹⁵

